

ULTRATHANE 42/40

Varnish, or Protective glaze-coat for
trafficable areas.

DESCRIPTION:

ULTRATHANE 42/40 is a moisture-curing aliphatic polyurethane containing a UV-absorber, which cures to give extremely tough and hardwearing films, resistance to yellowing and the effects of sunlight.

ULTRATHANE 42/40 may be used as supplied as a varnish, or protective glaze-coat for
trafficable areas.

Suggested application rates:

1st coat – 6 to 7mtrs per 1Ltr

2nd coat (once 1st coat fully cured) – 10 to 12mtrs per 1Ltr

Typical Properties:

Non-Volatile Content -	40%
Viscosity, Gardner-Holdt-	A-D
Colour, Gardner -	1
Specific Gravity -	0.98
Available NCO (solution) -	3%
Solvent -	Xylene / PGMA

SAFETY

Refer to Safety Data Sheet before Handling or use.

Distributors Welcome



To have an Expert Consultant contact you
To make a booking click here - <http://www.webstation.com.au/aimforms/>

Phone: 61 (07) 32071033

Email : info@aimgroup.com.au Website : www.aimgroup.com.au